

## **EPALLOY™ 7200MIBK90** **Modified Bisphenol A Epoxy Resin Solution**

### **DESCRIPTION**

**EPALLOY 7200MIBK90** is a blend of a modified liquid Bisphenol A diglycidyl ether resin in methylisobutyl ketone designed for fast cure, low viscosity, and low temperature applications.

**EPALLOY 7200MIBK90** will react with all epoxy resin curing agents to produce cured products with excellent chemical and mechanical properties. It is particularly recommended for use in coatings and primers for use in low temperature or fast cure applications.

### **APPLICATIONS**

- Fast Cure, High Solids Primers and Coatings
- Coatings/Primers for Low Temp Applications
- Fast Cure Chemical Resistant Coatings
- Accelerator for Standard Resin Systems

### **TYPICAL PROPERTIES**

Appearance	Clear, Clean
Viscosity @ 25°C, cps	3,000– 8,000
Epoxy Equivalent Weight, g/eq	208 –238
Solids Content (%)	89-91
Weight per Gallon @25°C, lbs.	9.6 +/- 0.1
Flash Point, Closed Cup °C (°F)	38 (100)

### **HEALTH & SAFETY PRECAUTIONS**

**EPALLOY 7200MIBK90** is not a primary skin irritant or sensitizer. However, as with any epoxy material, irritation can result from repeated or prolonged contact. The symptoms of this irritation may appear as a mild reddening or a more pronounced rash. It is, therefore, important to avoid skin contact where possible. Butyl rubber gloves, full eye protection and protective clothing are recommended.

Refer to **CVC Thermoset Specialties** Material Safety Data Sheet on **EPALLOY 7200MIBK90** for additional safety & handling information. The MSDS is revised as new data becomes available.

### **PACKAGING & AVAILABILITY**

**EPALLOY 7200MIBK90** is available in 55 gal. non-returnable steel drums (500 lbs. net) and 5 gal. plastic pails (45 lbs. net).

### **STORAGE**

**EPALLOY 7200MIBK90** will tend to increase in viscosity over time. Avoid storage in warm areas and keep out of direct sunlight. For longer shelf life, store **EPALLOY 7200MIBK90** at temperatures below 50°C.



**EPALLOY™ 7200MIBK90**

**An Emerald Performance Materials Company**

## **DISCLAIMER**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. CVC Thermoset Specialties shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond CVC's direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. **IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.**

CVC Thermoset Specialties—844 N. Lenola Road/Moorestown, NJ 08057  
An Emerald Performance Materials Company

© Copyright 2006 Emerald Performance Materials LLC. 6/2006

**CVC Thermoset Specialties**

844 North Lenola Road / Moorestown, NJ 08057 / Phone: 856-533-3000 / Fax: 856-533-3003 / [www.emeraldmaterials.com](http://www.emeraldmaterials.com)